

DELO-DUOPOX[®] 01 rapid

modified epoxy resin | 2C | room-temperature-curing

unfilled

Special features of product

- compliant with RoHS Directive 2015/863/EU

Typical area of use

- 40 - 80 °C

Curing

Curing time

until initial strength at rt approx. +23 °C tensile shear strength 1 - 2 MPa	8	min
until functional strength at rt approx. +23 °C tensile shear strength > 10 MPa	2	h
until final strength at rt approx. +23 °C	24	h

Processing

Mixing ratio A : B - weight	1 : 1	
Processing time after mixing		
in 3 g batch at rt approx. +23 °C	4	min
Storage life in unopened original container		
at +18 °C to +25 °C	12	month(s)

Technical properties


Color in cured condition in 1 mm layer thickness	yellowish
Transparency in cured condition in 1 mm layer thickness	transparent

Parameters


Density Component A DELO Standard 13 liquid	1.2	g/cm ³
--	-----	-------------------

Density <i>Component B DELO Standard 13 liquid</i>	1.13	g/cm ³
Viscosity <i>Component A liquid Viscosimeter</i>	63000	mPa·s
Viscosity <i>Component B liquid Viscosimeter</i>	21000	mPa·s
Tensile shear strength <i>by the criteria of DIN EN 1465 AI AI Pretreatment: sand-blasted at approx. +23 °C 24 h</i>	17	MPa
Tensile shear strength <i>by the criteria of DIN EN 1465 AI AI Pretreatment: sand-blasted at approx. +23 °C 168 h Measuring temperature: 100 °C</i>	1.5	MPa
Peel resistance <i>DELO Standard 38 Steel Steel Pretreatment: sand-blasted at approx. +23 °C 168 h</i>	2.6	N/mm
Tensile strength <i>by the criteria of DIN EN ISO 527 at approx. +23 °C 24 h</i>	35	MPa
Elongation at tear <i>by the criteria of DIN EN ISO 527 at approx. +23 °C 24 h</i>	3	%
Young's modulus <i>by the criteria of DIN EN ISO 527 at approx. +23 °C 24 h</i>	1800	MPa
Shore hardness D <i>by the criteria of DIN EN ISO 868 at approx. +23 °C 168 h</i>	40	
Water absorption <i>by the criteria of DIN EN ISO 62 Layer thickness: 4 mm at approx. +23 °C 168 h Type of storage: Media Medium: Distilled water Storage temperature: at approx. +23 °C Duration: 24 h</i>	1.9	wt. %
Decomposition temperature <i>DELO Standard 36 at approx. +23 °C 168 h</i>	200	°C

Tensile shear strength measured at the stated temperatures
Substrates: Al/Al, by the criteria of DIN EN 1465



Tensile shear strength after temperature storage
Substrates: Al/Al, by the criteria of DIN EN 1465



Converting table

°F	= (°C x 1.8) + 32	1 MPa	= 145.04 psi
1 inch	= 25.4 mm	1 GPa	= 145.04 ksi
1 mil	= 25.4 µm	1 cP	= 1 mPa·s
1 oz	= 28.3495 g	1 N	= 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Curing can be supported or accelerated by heat input. Additional heat input can change the physical properties of the product. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

You can find further details in the instructions for use.
The instructions for use are available on www.DELO-adhesives.com.
We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT