

DELO[®]-ML DB140

modified acrylate | 1C | UV- / VIS- / anaerobic-curing

free of solvents | tension-equalizing, very good temperature resistance, dual-curing, can be fixed quickly, high-strength

Special features of product

- compliant with RoHS Directive 2015/863/EU
- passes ANSI/UL 94 HB Flame Test

Function

- structural adhesive
- construction adhesive

Typical area of use

- -60 - 180 °C
- glass/metal bondings
- screw locking and thread sealing
- small metal areas with high fitting accuracy

Curing

Suitable lamp types	LED 365 nm, LED 400 nm, UVA
---------------------	-----------------------------

Intensity (maximum)	300	mW/cm ²
---------------------	-----	--------------------

Typical irradiation time

<i>intensity 200 mW/cm² LED 400 nm</i>	10	s
---	----	---

Curing time

<i>until initial strength at rt approx. +23 °C anaerobic on zinc-phosphated screws</i>	1 - 3	min
--	-------	-----

<i>until final strength at rt approx. +23 °C anaerobic on zinc-phosphated screws</i>	24	h
--	----	---

Processing

Conditioning time (typical)

<i>when stored in cold conditions in containers up to 50 ml</i>	30	min
---	----	-----

<i>when stored in cold conditions in containers up to 1,000 ml</i>	4	h
--	---	---

Storage life in unopened original container

<i>up to <= 600 ml at 0 °C to +10 °C</i>	6	month(s)
<i>up to <= 600 ml at 0 °C to +25 °C</i>	3	month(s)

Technical properties


Color in uncured condition	colorless
Transparency	transparent
Color in cured condition in 0.1 mm layer thickness	yellowish
Color in cured condition in 1 mm layer thickness	yellowish
Fluorescence	fluorescent

Parameters


Density <i>liquid</i>	1.09	g/cm ³
Viscosity <i>liquid Rheometer Shear rate: 10 1/s Gap: 200 µm</i>	900	mPa·s
Maximal durchhärtbare Schichtdicke <i>DELO Standard 20 White substrate 400 nm 200 mW/cm² 60 s</i>	4	mm
Tensile shear strength <i>by the criteria of DIN EN 1465 Al Al at approx. +23 °C 72 h</i>	6	MPa
Tensile shear strength <i>by the criteria of DIN EN 1465 Steel Steel at approx. +23 °C 72 h</i>	13	MPa
Compression shear strength <i>DELO Standard 5 Glass Glass 400 nm 200 mW/cm² 60 s</i>	30	MPa
Compression shear strength <i>by the criteria of ISO 10123 Steel shaft Steel hub at approx. +23 °C 1 h</i>	30	MPa
Compression shear strength <i>by the criteria of ISO 10123 Steel shaft Steel hub at approx. +23 °C 72 h</i>	40	MPa
Tensile strength <i>by the criteria of DIN EN ISO 527 400 nm 200 mW/cm² 90 s</i>	30	MPa

Elongation at tear <i>by the criteria of DIN EN ISO 527 400 nm 200 mW/cm² 90 s</i>	30	%
Young's modulus <i>by the criteria of DIN EN ISO 527 400 nm 200 mW/cm² 90 s</i>	900	MPa
Shore hardness D <i>by the criteria of DIN EN ISO 868 400 nm 200 mW/cm² 90 s</i>	74	
Glass transition temperature <i>DMTA 400 nm 200 mW/cm² 60 s</i>	120	°C
Coefficient of linear expansion <i>DELO Standard 26 TMA Evaluation T: 35 °C - 70 °C 400 nm 200 mW/cm² 60 s</i>	110	ppm/K
Coefficient of linear expansion <i>DELO Standard 26 TMA Evaluation T: 100 °C - 160 °C 400 nm 200 mW/cm² 60 s</i>	179	ppm/K
Shrinkage <i>DELO Standard 13 400 nm 200 mW/cm² 90 s</i>	8.7	vol. %
Water absorption <i>by the criteria of DIN EN ISO 62 Layer thickness: 4 mm 400 nm 200 mW/cm² 90 s Type of storage: Media Medium: Distilled water Storage temperature: at approx. +23 °C Duration: 24 h</i>	0.8	wt. %


Tensile strength after temperature storage, by the criteria of DIN EN ISO 527




Elongation at tear after temperature storage, by the criteria of DIN EN ISO 527




Young's modulus after temperature storage, by the criteria of DIN EN ISO 527




Compression shear strength after thermal storage, based on ISO 10123



Compression shear strength measured at the stated temperatures



Compression shear strength for determining the curing process shaft-to-hub bonding substrates: steel shaft/steel hub, by the criteria of DELO standard 31



Substrates: steel shaft / steel hub

Converting table

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

You can find further details in the instructions for use.

The instructions for use are available on www.DELO-adhesives.com.

We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT

DELO-ML DB140 | as of 22.04.2022 10:35 | Page 5 of 5

DELO Industrial Adhesives
Headquarters

▶ Germany · Windach / Munich ... www.DELO-adhesives.com

ADHESIVES

DISPENSING

CURING

CONSULTING

DELO