

# DELO DUALBOND® LT2345

**modified epoxy resin | 1C | light-fixable / heat-curing**

free of solvents | low outgassing, can be fixed quickly | light-fixable, low-temperature-curing

### Special features of product

- low-outgassing according to ASTM E 595-93 (also known as NASA outgassing test)
- halogen-free according to IEC 61249-2-21
- compliant with RoHS Directive 2015/863/EU

### Function

- electronic adhesive

### Typical area of use

- -40 - 180 °C

### Curing

Suitable lamp types LED 365 nm, LED 400 nm

Typical light fixation time

*intensity 1,000 mW/cm<sup>2</sup>  
LED 365 nm* 1 - 3 s

Typical curing time

*at +80 °C  
in air convection oven* 50 min

*at +100 °C  
in air convection oven* 20 min

### Processing

Conditioning time (typical)

*when stored in cold conditions  
in containers up to 10 ml* 0.5 h

Processing time

*in standard climate +23 °C / 50 % r. h.* 72 h

Storage life in unopened original container

*at -25 °C to -15 °C* 5 month(s)

**Technical properties**

Color in cured condition in 1 mm layer thickness	orange
Transparency in cured condition in 1 mm layer thickness	opaque

**Parameters**

Density <i>Based on DIN 66137-2</i>	1.52	g/cm <sup>3</sup>
Viscosity <i>Rheometer   Shear rate: 10 1/s   Gap: 500 µm</i>	65000	mPa·s
Compression shear strength <i>DELO Standard 5   <b>Al</b>   <b>Al</b>   Pretreatment: sand-blasted   100 °C   60 min</i>	60	MPa
Compression shear strength <i>DELO Standard 5   <b>PA6</b>   <b>PA6</b>   Pretreatment: Annealing, Desiccator   100 °C   60 min</i>	18	MPa
Compression shear strength <i>DELO Standard 5   <b>Ni</b>   <b>Ni</b>   Pretreatment: Laser   100 °C   60 min</i>	52	MPa
Die shear strength <i>DELO Standard 30   Chip 1 mm x 1 mm   <b>Si</b>   25 mm x 15 mm   <b>Au</b>   100 °C   60 min</i>	16	N
Die shear strength <i>DELO Standard 30   Chip 1 mm x 1 mm   <b>Si</b>   20 mm x 20 mm x 5 mm   <b>FR4</b>   Pretreatment: Annealing   100 °C   60 min</i>	62	N
Tensile strength <i>Based on DIN EN ISO 527   100 °C   60 min</i>	58	MPa
Elongation at tear <i>Based on DIN EN ISO 527   100 °C   60 min</i>	1	%
Young's modulus <i>DMTA   400 nm   1000 mW/cm<sup>2</sup>   1 s   Plus   100 °C   60 min</i>	4500	MPa
Shore hardness D <i>Based on DIN EN ISO 868   400 nm   1000 mW/cm<sup>2</sup>   1 s   Plus   100 °C   60 min</i>	90	
Glass transition temperature <i>DMTA   400 nm   1000 mW/cm<sup>2</sup>   1 s   Plus   100 °C   60 min</i>	135	°C
Coefficient of linear expansion <i>DELO Standard 26   TMA   Evaluation T: 130 °C - 190 °C   400 nm   1000 mW/cm<sup>2</sup>   1 s   Plus   100 °C   60 min</i>	108	ppm/K

Coefficient of linear expansion <i>DELO Standard 26   TMA   Evaluation T: -30 °C - 40 °C   400 nm   1000 mW/cm²   1 s   Plus   100 °C   60 min</i>	30	ppm/K
Shrinkage <i>DELO Standard 13   400 nm   1000 mW/cm²   1 s   Plus   100 °C   60 min</i>	3	vol. %
Water absorption <i>Based on DIN EN ISO 62   400 nm   1000 mW/cm²   1 s   Plus   100 °C   60 min   Type of storage: Media   Medium: Distilled water   Storage temperature: at approx. +23 °C   Duration: 24 h</i>	0.1	wt. %

**Converting table**

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

**General curing and processing information**

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. The heating time of the components must be added to the actual curing time. It depends on component size and type of heat input. The specified curing temperature must be reached directly at the adhesive. Increasing or decreasing the curing temperature and / or irradiation intensity and / or irradiation time shortens or prolongs the curing time and can lead to changed physical properties. Depending on the adhesive quantity used, exothermic reaction heat is generated which can lead to overheating. In this case, a lower curing temperature is to be selected. All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer. Optional pre-fixation is performed with light. Heat curing is mandatory. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

**General**

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

### **Instructions for use**

You can find further details in the instructions for use.

The instructions for use are available on [www.DELO-adhesives.com](http://www.DELO-adhesives.com).

We will be pleased to send them to you on demand.

### **Occupational health and safety**

See material safety data sheet.

### **Specification**

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

## **CONTACT**

DELO DUALBOND LT2345 | as of 10.12.2020 11:04 | Page 4 of 4

**DELO** Industrial Adhesives  
Headquarters

▶ Germany · Windach / Munich ... [www.DELO-adhesives.com](http://www.DELO-adhesives.com)

ADHESIVES

DISPENSING

CURING

CONSULTING

**DELO**