

### **DELO® PHOTOBOND® GB310**

UV-curing acrylate adhesive, low viscosity

#### **Base**

- modified urethane acrylate
- one-component, solvent-free

#### **Use**

- preferably for interior glass/glass and glass/metal bondings
- very good capillary properties
- the cured product is normally used in a temperature range of -40 °C to +120 °C; depending on the application, other limits may be more reasonable
- compliant with RoHS directive 2015/863/EU

#### **Processing**

- the adhesive is supplied ready for use; in case of cool storage, it must be ensured that the container is conditioned to room temperature before use
- the containers are conditioned at room temperature (+18 °C to +25 °C); the conditioning time is approx. 0.5 h for containers up to 50 ml and approx. 4 h for containers up to 1,000 ml; additional heat addition is not allowed
- the adhesive can be applied by dispensing
- the surfaces to be bonded must be dry as well as free of dust, grease and other contaminations
- dispensing valves and product-bearing elements must be carefully cleaned before use, residues of other products must be completely removed; isopropanol is recommended to remove DELO PHOTOBOND residues
- for further information please refer to our instructions for use DELO PHOTOBOND and the brochure "Light Curing"

#### **Curing**


- curing with UV light in a wavelength range from 320 to 400 nm. DELOLUX LED curing lamps are especially suitable as per the chart below. All standard DELOLUX HID discharge lamps are also suitable
- increased intensities shorten the required irradiation time, lower intensities prolong it

Lamp type	DELOLUX 20 / 50 / 80		
Wavelength [nm]	365	400	460
Suitability	++	-	-

- not suitable + suitable ++ especially suitable

## **Absorption spectrum**

photoinitiation system in acrylate matrix



## **Curing parameters**

- dependent on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer

## **Technical data**

### *Color*

cured in a layer thickness of approx. 0.1 mm

colorless clear

### **Density [g/cm<sup>3</sup>]**

at room temperature (approx. 23 °C)

1.0

### **Viscosity [mPas]**

at 23 °C, Brookfield spindle/rpm 3/100

100

### **Minimal curing time [s]**

DELO Standard 23, UVA intensity: 60 mW/cm<sup>2</sup>, DELOLUXcontrol

20

### **Compression shear strength glass/glass [MPa]**

DELO Standard 5

UVA intensity: 55 - 60 mW/cm<sup>2</sup>, DELOLUXcontrol, irradiation time: 60 s

34

### **Compression shear strength glass/Al [MPa]**

DELO Standard 5

UVA intensity: 55 - 60 mW/cm<sup>2</sup>, DELOLUXcontrol, irradiation time: 60 s

40

### **Compression shear strength glass/PC [MPa]**

DELO Standard 5

UVA intensity: 55 - 60 mW/cm<sup>2</sup>, DELOLUXcontrol, irradiation time: 60 s

4

### **Compression shear strength glass/PMMA [MPa]**

DELO Standard 5

UVA intensity: 55 - 60 mW/cm<sup>2</sup>, DELOLUXcontrol, irradiation time: 60 s

4

### **Tensile strength [MPa]**

DIN EN ISO 527

33

### **Elongation at tear [%]**

DIN EN ISO 527

4

### **Young's modulus [MPa]**

DIN EN ISO 527

1600

### **Shore hardness D**

according to DIN EN ISO 868

77

### **Decomposition temperature [°C]**

DELO Standard 36

190

### **Glass transition temperature [°C]**

rheometer

120

Coefficient of linear expansion [ppm/K] in a temperature range of +25 to +140 °C	168
Shrinkage [vol. %] DELO Standard 13	10
Water absorption [weight %] according to DIN EN ISO 62, 24 h at room temperature (approx. 23 °C)	0.4
Index of refraction	1.503
Storage life at room temperature (0 °C to +25 °C) in unopened original container	12 months

## **Instructions and advice**

### **General**

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

### **Instructions for use**

The instructions for use of DELO PHOTOBOND are available on: [www.DELO.de](http://www.DELO.de). We will be pleased to send them to you on demand.

### **Occupational health and safety**

Irritating to eyes, respiratory system and skin. In case of contact with eyes, immediately rinse with plenty of water and consult physician. On contact with skin, immediately wash off with plenty of soap and water. For further details see material safety data sheet.

### **Specification**

The properties in italics are part of the specification. Ranges with clear limits are defined for them and others, where applicable. In the course of the QA test, each batch is tested for these properties and the maintenance of the limits is ensured. The measuring methods used can deviate from those specified in the data sheet. Details can be found in the QA test report.