

DELO[®] PHOTOBOND[®] LA4890

modified urethane polymer | 1C | light-activated / humidity-curing

free of solvents | thixotropic | preactivated

Special features of product

- compliant with RoHS Directive 2015/863/EU

Typical area of use

- 40 - 120 °C

Curing

Suitable lamp types LED 400 nm, LED 460 nm

Typical preactivation time

*intensity 300 mW/cm²
LED 400 nm* 6 s

*intensity 400 mW/cm²
LED 460 nm* 6 s

Typical open time

LED 400 nm 10 - 40 s

LED 460 nm 10 - 60 s

Processing

Conditioning time (typical)

*when stored in cold conditions
in containers up to 50 ml* 30 min

*when stored in cold conditions
in containers up to 1,000 ml* 4 h

Storage life in unopened original container

*up to <= 1 l
at 0 °C to +10 °C* 6 month(s)

Technical properties

Color in uncured condition yellowish

Color in cured condition in 0.1 mm layer thickness colorless

Fluorescence fluorescent

Parameters

Density 1.34 g/cm³
Based on DIN 66137-2 | liquid

Viscosity 85000 mPa·s
liquid | Rheometer | Shear rate: 2 1/s | Gap: 500 µm

Maximum curable layer thickness 1.2 mm
460 nm | 400 mW/cm² | 6 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %

Maximum curable layer thickness 0.8 mm
400 nm | 300 mW/cm² | 6 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %

Compression shear strength 2 MPa
*DELO Standard 5 | **AI | AI** | Preactivation | 400 nm | 200 mW/cm² | 4 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Compression shear strength 3 MPa
*DELO Standard 5 | **PC-ABS | PC-ABS** | Preactivation | 400 nm | 300 mW/cm² | 6 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Compression shear strength 3 MPa
*DELO Standard 5 | **Glass | Glass** | Preactivation | 400 nm | 200 mW/cm² | 4 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Compression shear strength 3 MPa
*DELO Standard 5 | **PMMA | PMMA** | Preactivation | 400 nm | 200 mW/cm² | 4 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Compression shear strength 3 MPa
*DELO Standard 5 | **Glass | PA66** | Preactivation | 400 nm | 200 mW/cm² | 4 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Compression shear strength 3 MPa
*DELO Standard 5 | **PC | PC** | Preactivation | 400 nm | 200 mW/cm² | 4 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Peel resistance 26 N/cm
***PC | PC** | Preactivation | 400 nm | 200 mW/cm² | 4 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %*

Tensile strength 3 MPa
Based on DIN EN ISO 527 | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 168 h | Rel. air humidity: 50 %

Elongation at tear 210 %
Based on DIN EN ISO 527 | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 168 h | Rel. air humidity: 50 %

Young's modulus < 10 MPa
 DMTA | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %

Shore hardness A 50
 Based on DIN EN ISO 868 | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 168 h | Rel. air humidity: 50 %

Glass transition temperature - 80 °C
 DMTA | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 72 h | Rel. air humidity: 50 %

Shrinkage 1 vol. %
 DELO Standard 13 | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 168 h | Rel. air humidity: 50 %

Water absorption 0.5 wt. %
 Based on DIN EN ISO 62 | 400 nm | 200 mW/cm² | 60 s | Plus | at approx. +23 °C | 168 h | Rel. air humidity: 50 % | Type of storage: Media | Medium: Distilled water | Storage temperature: at approx. +23 °C | Duration: 24 h

Converting table

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Increasing or decreasing the curing temperature and / or irradiation intensity and / or irradiation time shortens or prolongs the curing time and can lead to changed physical properties. A short irradiation time (preactivation time) results in an open time within which opaque components can be joined. The product cures completely after preactivation by humidity at room temperature. Air humidity is mandatory for curing. All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.
 All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

You can find further details in the instructions for use.
 The instructions for use are available on www.DELO-adhesives.com.
 We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT