

### DELO® PHOTOBOND® OC4022

UV- and light curing acrylate adhesive, low viscosity

#### Base

- modified acrylate
- one-component, solvent-free

#### Use

- optically clear adhesive for full area glass to glass bonding, e.g. display or touch panel bonding, especially for automotive applications
- highly flexible, tension-equalizing
- the cured product is normally used in a temperature range of -40 °C to +85 °C; depending on the application, other limits may be more reasonable
- compliant with RoHS directive 2015/863/EU
- halogen-free according to IEC 61249-2-21

#### Processing

- the adhesive is supplied ready for use; in case of cool or refrigerated storage, it must be ensured that the container is conditioned to room temperature before use
- the adhesive can be applied by dispensing
- the surfaces to be bonded must be dry as well as free of dust, grease and other contaminations
- dispensing valves and product-bearing elements must be carefully cleaned before use, residues of other products must be completely removed; isopropanol is recommended to remove DELO PHOTOBOND residues
- for further information please refer to our instructions for use DELO PHOTOBOND, the brochure "Light Curing" and the brochure "Optically clear Adhesives"

#### Curing


- curing with UV light or visible light in a wavelength range from 320 to 420 nm. DELOLUX LED curing lamps are especially suitable as per the chart below. All standard DELOLUX HID discharge lamps are also suitable
- increased intensities shorten the required irradiation time, lower intensities prolong it

Lamp type	DELOLUX 20 / 50 / 80		
Wavelength [nm]	365	400	460
Suitability	+	++	-

- not suitable + suitable ++ especially suitable

## Absorption spectrum

- photoinitiation system in acrylate matrix



## Curing parameters

- dependent on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer  
- at the adhesive, the effective curing intensity should lie between 50 and 200mW/cm<sup>2</sup> taking into consideration the transmittance of the joining parts

## Additional technical information

<http://www.delo.de/delo/3QRT7/?1MLnrb1a>

## Technical data

<b>Color</b> cured in a layer thickness of approx. 0.1 mm	colorless clear
<b>Density [g/cm<sup>3</sup>]</b>	1.0
<b>Viscosity [mPas]</b> at 23 °C, rheometer	1000
<b>Recommended irradiation time [s]</b> DELO-Standard 23, LED 400nm, intensity: 60 mW/cm <sup>2</sup> DELOLUXcontrol	30
<b>Recommended irradiation time [s]</b> DELO-Standard 23, LED 400nm, intensity: 200 mW/cm <sup>2</sup> DELOLUXcontrol	20
<b>Curable layer thickness [mm]</b> DELO Standard 20 LED intensity: 60mW/cm <sup>2</sup> DELOLUScontrol, LUX80/400, irradiation time: 30s	<4
<b>Stud pull strength glass/glass [MPa]</b> DELO Standard 48	0.5
<b>Shear modulus [kPa]</b> DELO Standard 45	10
<b>Shrinkage [vol. %]</b> DELO Standard 13	1.8
<b>initial b* value</b> DELO Standard 25 Reflection measurement at 1.5 mm layer thickness	1.3
<b>Index of refraction</b> cured product	1.482

Dielectric constant  
relative permittivity  $\epsilon_r$   
RF I-V method, extrapolated value at 1 MHz

6


Glass transition temperature [°C]  
DMTA

-53

Haze [%]  
ASTMD1003, Haze-Gard plus, 1mm layer thickness

0.2

### Transmittance



Storage life at room temperature in original container

4 weeks

Storage life  
at 0°C to +10°C in unopened original container

6 months

## **Instructions and advice**

### General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

### Instructions for use

The instructions for use of DELO DUALBOND are available on: [www.DELO.de](http://www.DELO.de). We will be pleased to send them to you on demand.

### Occupational health and safety

see material safety data sheet

### Specification

The properties in italics are part of the specification. Ranges with clear limits are defined for them and others, where applicable. In the course of the QA test, each batch is tested for these properties and the maintenance of the limits is ensured. The measuring methods used can deviate from those specified in the data sheet. Details can be found in the QA test report.