

DELO[®] PHOTOBOND[®] PS4130

modified acrylate | 1C | UV- / VIS-curing

free of solvents | filled | pressure-sensitive adhesive

Special features of product

- compliant with RoHS Directive 2015/863/EU
- compliant with limits of VOC content in adhesive acc. to GB33372-2020

Typical area of use

- -40 - 120 °C

Curing

Suitable lamp types LED 365 nm, LED 400 nm

Typical irradiation time

*intensity 200 mW/cm²
LED 400 nm* 9 s

*intensity 1,000 mW/cm²
LED 400 nm* 3 s

Typical pressing time

*Contact pressure
0.1 MPa* 3 s

Typical tape phase

*intensity 200 mW/cm²
LED 400 nm* 21 d

Processing

Typical adhesive application needle dispensing, jetting

Conditioning time (typical)

*when stored in cold conditions
in containers up to 50 ml* 1 h

*when stored in cold conditions
in containers up to 600 ml* 5 h

Storage life in unopened original container

at 0 °C to +10 °C 6 month(s)

Technical properties

Color in uncured condition	yellowish
Color in cured condition in 0.1 mm layer thickness	yellowish
Color in cured condition in 1 mm layer thickness	yellowish
Fluorescence	blue fluorescent
Density	1.03 g/cm ³

Parameters

Viscosity <i>liquid Rheometer Shear rate: 2 1/s Gap: 500 µm</i>	19000	mPa·s
Peel resistance <i>DELO Standard 34 PC PC 400 nm 500 mW/cm² 10 s</i>	6	N/cm
Peel resistance <i>DELO Standard 34 PEI PEI 400 nm 500 mW/cm² 10 s</i>	9	N/cm
Peel resistance <i>DELO Standard 34 PET PET 400 nm 500 mW/cm² 10 s</i>	6	N/cm
Stud pull strength <i>DELO Standard 48 AI AI 400 nm 500 mW/cm² 10 s</i>	1	MPa
Stud pull strength <i>DELO Standard 48 Ni Ni 400 nm 500 mW/cm² 10 s</i>	0.3	MPa
Stud pull strength <i>DELO Standard 48 PC PC 400 nm 500 mW/cm² 10 s</i>	0.4	MPa
Stud pull strength <i>DELO Standard 48 PEI PEI 400 nm 500 mW/cm² 10 s</i>	0.4	MPa

Converting table

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Increasing or decreasing the curing temperature and / or irradiation intensity and / or irradiation time shortens or prolongs the curing time and can lead to changed physical properties. All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified. The typical irradiation time results in a tape phase within which these components can be joined. During this tape phase, the adhesive is pressure-sensitive.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

You can find further details in the instructions for use.

The instructions for use are available on www.DELO-adhesives.com.

We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT

DELO PHOTOBOND PS4130 | as of 15.01.2021 07:47 | Page 3 of 3

DELO Industrial Adhesives
Headquarters

▶ Germany · Windach / Munich ... www.DELO-adhesives.com