

DELO® PHOTOBOND® PS4130

UV- and light curing acrylate adhesive, medium viscosity

Base

- modified acrylate
- one-component, solvent-free

Use

- very soft and flexible adhesive for pressure sensitive applications
- The adhesive needs to be cured through light after dispensing it to the customer part. Afterwards the substrates can be joined.
- generally, the product is used in a temperature range of -40 °C up to +120 °C; related to the application, other limits may be more reasonable
- compliant with RoHS directive 2015/863/EU
-

Processing

- the adhesive is supplied ready for use; in case of cool storage, it must be ensured that the container is conditioned to room temperature before use
- the containers are conditioned at room temperature (+18 °C to +25 °C); the conditioning time is approx. 0.5 h for containers up to 50 ml and approx. 4 h for containers up to 1,000 ml; additional heat addition is not allowed
- the adhesive can be applied by dispensing
- the surfaces to be bonded must be dry as well as free of dust, grease and other contaminations
- dispensing valves and product-bearing elements must be carefully cleaned before use, residues of other products must be completely removed; Isopropanol is recommended to remove DELO PHOTOBOND residues
- for further information please refer to our instructions for use DELO PHOTOBOND and the brochure "Light Curing"

Curing

- with UV light or visible light in a wavelength range of 320 - 450 nm

Curing parameters

- dependent on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer

Technical data

Color
uncured

yellowish and fluorescent

Density [g/cm³]
at room temperature (approx. 23 °C)

1.03

DELO Industrial Adhesives
DELO-Allee 1
86949 Windach · Germany
Phone +49 8193 9900-0
Fax +49 8193 9900-144
info@DELO.de · www.DELO.de

Viscosity [mPas] at 23 °C, rheometer, shear rate 2 1/s	19000
Recommended irradiation time [s] DELO Standard 55, LED 400nm, intensity: 200 mW/cm ² , DELOLUXcontrol layer thickness 0.1 mm	7
Recommended irradiation time [s] DELO Standard 55, LED 400nm, intensity: 1000 mW/cm ² , DELOLUXcontrol layer thickness 0.1 mm	3
Stud pull strength PC/PC [MPa] DELO Standard 48	0.4
Stud pull strength AL/AL [MPa] DELO Standard 48	1.0
Stud pull strength PEI/PEI [MPa] DELO Standard 48	0.4
Stud pull strength Ni/Ni [MPa] DELO Standard 48	0.3
peeling resistance PC/PC [N/cm] DELO Standard 34	6
<i>peeling resistance PAR/PAR [N/cm]</i> DELO Standard 34	14
peeling resistance PEI/PEI [N/cm] DELO Standard 34	9
peeling resistance PET/PET [N/cm] DELO Standard 34	6
Storage life at room temperature (approx. 23 °C) in unopened original container	6 months

Instructions and advice

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

The instructions for use of DELO PHOTOBOND are available on: www.DELO.de. We will be pleased to send them to you on demand.

Occupational health and safety

see material safety data sheet

Specification

The properties in italics are part of the specification. Ranges with clear limits are defined for them and others, where applicable. In the course of the QA test, each batch is tested for these properties and the maintenance of the limits is ensured. The measuring methods used can deviate from those specified in the data sheet. Details can be found in the QA test report.