

# DELO<sup>®</sup>-GUM 3697

**acetic-acid-decomposing silicone rubber | 1C | room-temperature-curing**

free of solvents | tension-equalizing, self-leveling, very good temperature resistance

### Special features of product

- compliant with RoHS Directive 2015/863/EU
- RTV-1 silicone

### Typical area of use

- -50 - 180 °C

### Curing

Skin formation time

*in standard climate +23 °C / 50 % r. h.*

10 - 20 min

Cured layer per 24 h

*at +23 °C / 50 % relative air humidity*

2 mm

### Processing

Storage life in unopened original container

*up to <= 310 ml  
at +15 °C to +30 °C*

12 month(s)

### Technical properties

Color in cured condition in 1 mm layer thickness

whitish

Transparency in cured condition in 1 mm layer thickness

transparent

Decomposition product

acetic acid

### Parameters

Density

*DELO Standard 13 | Liquid*

1.1 g/cm<sup>3</sup>

Viscosity

*Based on DIN 54453 | Liquid | Viscosimeter*

350000

Tensile strength <i>Based on DIN EN ISO 527   at approx. +23 °C   9 d</i>	5	MPa
Elongation at tear <i>Based on DIN EN ISO 527   at approx. +23 °C   9 d</i>	500	%
Shore hardness A <i>Based on DIN EN ISO 868   at approx. +23 °C   7 d</i>	28	
Shrinkage <i>DELO Standard 13   Liquid</i>	3	vol. %
Water absorption <i>Based on DIN EN ISO 62   at approx. +23 °C   7 d   Type of storage: Media   Medium: Distilled water   Duration: 24 h</i>	0.06	wt. %
Volume resistivity <i>Based on VDE 0303-3   Liquid</i>	>1xE13	Ohm·cm
Dielectric strength <i>Based on VDE 0303-2   Liquid</i>	21	kV/mm
Creep resistance CTI M <i>Based on VDE 0303-1   Liquid</i>	600	

**Converting table**

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

**General curing and processing information**

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Unless otherwise specified, the values were measured after 168 h at approx. 23 °C / 50 % r. h., and the values of heat-cured samples were measured after 24 h at approx. 23 °C / 50 % r. h. Curing requires a minimum air humidity of 50 % r. h.

**General**

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer

deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

### **Instructions for use**

You can find further details in the instructions for use.

The instructions for use are available on [www.DELO-adhesives.com](http://www.DELO-adhesives.com).

We will be pleased to send them to you on demand.

### **Occupational health and safety**

See material safety data sheet.

### **Specification**

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

## **CONTACT**

DELO-GUM 3697 | as of 01.07.2020 07:00 | Page 3 of 3

**DELO** Industrial Adhesives  
Headquarters

▶ Germany · Windach / Munich ... [www.DELO-adhesives.com](http://www.DELO-adhesives.com)

ADHESIVES

DISPENSING

CURING

CONSULTING

**DELO**