

# DELO<sup>®</sup> PHOTOBOND<sup>®</sup> PB437

**modified acrylate | 1C | UV- / VIS-curing**

free of solvents | thixotropic

## Special features of product

- compliant with RoHS Directive 2015/863/EU

## Typical area of use

- 40 - 120 °C
- mixed bondings with plastics
- glass/metal bondings

## Curing

Suitable lamp types LED 365 nm, LED 400 nm

Typical irradiation time

*intensity 200 mW/cm<sup>2</sup>* 5 s  
*LED 400 nm*

*intensity 1000 mW/cm<sup>2</sup>* 3 s  
*LED 400 nm*

## Processing

Storage life in unopened original container

*at +18 °C to +25 °C* 12 month(s)

## Technical properties

Color in uncured condition colorless

Transparency transparent

Color in cured condition in 0.1 mm layer thickness colorless

Color in cured condition in 1 mm layer thickness colorless

Filler information unfilled

## Parameters

Density 1.03 g/cm<sup>3</sup>  
*liquid*

Viscosity <i>by the criteria of DIN EN 12092   liquid   Viscosimeter</i>	8000	mPa·s
Viscosity <i>liquid   Rheometer   Shear rate: 10 1/s   Gap: 500 µm</i>	3200	mPa·s
Compression shear strength <i>DELO Standard 5   <b>Glass</b>   <b>Al</b>   60 mW/cm²   60 s</i>	30	MPa
Compression shear strength <i>DELO Standard 5   <b>Glass</b>   <b>Stainless steel</b>   60 mW/cm²   60 s</i>	31	MPa
Compression shear strength <i>DELO Standard 5   <b>Glass</b>   <b>Glass</b>   60 mW/cm²</i>	31	MPa
Compression shear strength <i>DELO Standard 5   <b>Glass</b>   <b>PC</b>   60 mW/cm²   60 s</i>	14	MPa
Compression shear strength <i>DELO Standard 5   <b>Glass</b>   <b>PMMA</b>   60 mW/cm²   60 s</i>	8	MPa
Compression shear strength <i>DELO Standard 5   <b>PC</b>   <b>Al</b>   60 mW/cm²   60 s</i>	9	MPa
Compression shear strength <i>DELO Standard 5   <b>PC</b>   <b>PC</b>   60 mW/cm²   60 s</i>	22	MPa
Compression shear strength <i>DELO Standard 5   <b>PMMA</b>   <b>PA6</b>   60 mW/cm²   60 s</i>	12	MPa
Compression shear strength <i>DELO Standard 5   <b>PMMA</b>   <b>PMMA</b>   60 mW/cm²   60 s</i>	9	MPa
Tensile strength <i>by the criteria of DIN EN ISO 527   60 mW/cm²   90 s</i>	21	MPa
Elongation at tear <i>by the criteria of DIN EN ISO 527   60 mW/cm²   90 s</i>	110	%
Young's modulus <i>by the criteria of DIN EN ISO 527   60 mW/cm²   90 s</i>	520	MPa
Shore hardness D <i>by the criteria of DIN EN ISO 868   60 mW/cm²   90 s</i>	65	
Glass transition temperature <i>DELO Standard 24   Rheometer   60 mW/cm²   60 s</i>	114	°C
Coefficient of linear expansion <i>TMA   Evaluation T: 25 °C - 140 °C   60 mW/cm²   60 s</i>	184	ppm/K

Shrinkage <i>DELO Standard 13   60 mW/cm<sup>2</sup>   60 s</i>	9	vol. %
Water absorption <i>by the criteria of DIN EN ISO 62   60 mW/cm<sup>2</sup>   60 s   Type of storage: Media   Medium: Distilled water   Storage temperature: at approx. +23 °C</i>	1	wt. %
Decomposition temperature <i>DELO Standard 36   60 mW/cm<sup>2</sup>   60 s</i>	195	°C
Volume resistivity <i>by the criteria of DIN EN 62631-3-1</i>	> 1E13	Ohm·cm

**Converting table**

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

**General curing and processing information**

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Increasing or decreasing the curing temperature and / or irradiation intensity and / or irradiation time shortens or prolongs the curing time and can lead to changed physical properties. All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

**General**

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

### Instructions for use

You can find further details in the instructions for use.  
The instructions for use are available on [www.DELO-adhesives.com](http://www.DELO-adhesives.com).  
We will be pleased to send them to you on demand.

### Occupational health and safety

See material safety data sheet.

### Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

## CONTACT